



SORBERG®

build by passion



TECHNICAL DATA SHEET

1. Unique identification code of the product-type:

SORBERG SOLID

2. Manufacturer:

SORBERG s.c., ul. Krasickiego 1A/35, 99-200 Poddębice, Polska

3. Application:

SORBERG SOLID is diffuse-open membrane designed as house wrap, which goes under the external roofing. Membrane **SORBERG SOLID** is totally waterproof, protects thermal insulation against rain or snow from the outside and also it is an excellent wind barrier designed a cover walls in framed structures.

The product can be used in all ventilated and non-ventilated roofs, under a variety of roofing (eg. ceramic tile, concrete tile, metal tiles, etc.).

The membrane should be protected from direct exposure to UV radiation within one month of installation and from the effects of scattered radiation - max. within 3 months, by installation of insulation on the inside.

4. Characteristics:

Characteristics		Test metod	Unit	Declared value
Dimensions	width *	EN 1848-2	m	1,5 ± 0,5%
	length of the the roll *		m	50 (-0/+2%)
	thickness	EN 1849-2	mm	0,4
Weight of roll		-----	kg	8,625 ± 15%
Mass per unit area		EN 1849-2	g/m ²	115 ± 15%
Reaction to fire		EN ISO 11925-2	-	Class E
Watertightness (2 kPa)		EN 1928	-	Class W1
Watertightness after artificial ageing		EN 1296, EN 1928	-	Class W1
Resistance to tearing	in longitudinal direction	EN 12310-1	N	130 (+50;-50)
	in transverse direction		N	130 (+50;-50)
Tensile strength	in longitudinal direction	EN 12311-2	N/50mm	190 (+50;-50)
	in transverse direction		N/50mm	100 (+30;-30)
Elongation at break	in longitudinal direction		%	80 (+40;-40)
	in transverse direction		%	150 (+50;-50)
Tensile strength after artificial ageing	in longitudinal direction	EN 1296	N/50mm	135 (+35; -35)
	in transverse direction	EN 1297	N/50mm	70 (+20;-20)
Elongation at break after artificial ageing	in longitudinal direction		%	60 (+20;-20)
	in transverse direction	EN 12311-2	%	100 (+35;-35)
Water vapour resistance		EN 1931	m ² sPa/kg	2,2 *10 ⁸ ± 20%
Vapour permeability		EN 1931	(g/m ²)/24h	>1700
S _d		EN 1931	m	0,02 (-0,01;+0,03)
Application temperature range		-----	°C	-30 ÷ 80
Dangerous substances		-----	-	NPD

*or as agreed with the customer